

AMENDMENTS TO THE CLAIMS

Claim 1 (Original) A smelter feedstock composition from which metal values are recoverable in a smelter, said composition consisting essentially of comminuted cermet.

Claim 2 (Original) The composition of claim 1 wherein said cermet is isolated from inert used anode, inert unused anode, inert anode manufacturing residue, or combinations thereof.

Claim 3 (Original) The composition of claim 2 which further comprises a fluxing additive which facilitates smelting of said composition in a smelter.

Claim 4 (Cancelled)

Claim 5 (Currently Amended) The composition of claim ~~[[4]]~~ 3 which has been roasted under oxidizing conditions to ~~oxide~~ oxidize a portion of said composition.

Claim 6 (Original) The composition of claim 3 wherein said fluxing additive is selected from the group consisting of alumina, lime, silica, magnesia, iron, metal hydroxide and mixtures thereof.

Claim 7 (Currently Amended) The composition of claim 6 wherein said metal hydroxide is ~~an~~ at least one hydroxide of a metal selected from the group consisting of copper, nickel, cobalt, precious metal and platinum group metal.

Claim 8 (Original) The composition of claim 1 which further comprises an ore concentrate.

Claim 9 (Original) The composition of claim 2 which further comprises an ore concentrate.

Claim 10 (Original) The composition of claim 3 which further comprises an ore concentrate.

Claim 11 (Original) A method for recovering metal values from smelter feedstock which comprises smelting said feedstock in a smelter which produces a first component containing said metal and a second component which is slag; and recovering said metal values from said first component; wherein said smelter feedstock composition consists essentially of comminuted cermet.

Claim 12 (Original) The method of claim 11 wherein said cermet is isolated from inert used anode, inert unused anode, inert anode manufacturing residue, or combinations thereof.

Claim 13 (Original) The method of claim 12 wherein said smelter feedstock composition further comprises a fluxing additive to facilitate smelting of said feedstock composition in a smelter.

Claim 14 (Cancelled)

Claim 15 (Currently Amended) The method of claim ~~[[14]]~~ 13 wherein said smelter feedstock composition has been roasted under oxidizing conditions to oxidize a portion of said feedstock composition.

Claim 16 (Original) The method of claim 13 wherein said fluxing additive is selected from the group consisting of alumina, lime, silica, magnesia, iron, metal hydroxide and mixtures thereof.

Claim 17 (Original) The method of claim 16 wherein said metal hydroxide is an hydroxide of a metal selected from the group consisting of copper, nickel, cobalt, precious metal, platinum group metal and mixtures thereof.

Claim 18 (Original) The method of claim 11 wherein said smelter feedstock further comprises an ore concentrate.

Claim 19 (Original) The method of claim 12 wherein said smelter feedstock further comprises an ore concentrate.

Claim 20 (Original) A method for making smelter feedstock which comprises isolating cermet from inert used anode, inert unused anode, inert anode manufacturing residue or combinations thereof; and comminuting said cermet.

Claim 21 (Original) The method of claim 20 which further comprises adding a fluxing additive to said comminuted cermet.

Claim 22 (Original) A method for treating inert anodes which comprises isolating cermet from said anodes; comminuting said isolated cermet to produce comminuted cermet; optionally using some or all of said comminuted cermet as a component in the manufacturing of inert anodes which contain cermet as a component thereof; and using all or a portion of said comminuted cermet as smelter feedstock in a smelting procedure to thereby recover metal values from said cermet.

Claim 23 (Original) The method of claim 22 wherein said smelter feedstock further comprises ore concentrate.

Claim 24 (Original) The method of claim 23 wherein said smelter feedstock further comprises a fluxing additive to aid in said smelting.